

# Technical Data Sheet

## DESCRIPTION OF THE PRODUCT

Natural, Ground Calcium Carbonate, Produced from high purity limestone.

## CHEMICAL ANALYSIS OF THE RAW MATERIAL

CaCO <sub>3</sub>	99.50 %	(BSI 795-1965)		
Fe <sub>2</sub> O <sub>3</sub>	0.052 %	MgO	0.17 %	
P <sub>2</sub> O <sub>5</sub>	0.16 %	Na <sub>2</sub> O	0.00 %	
SiO <sub>2</sub>	0.12 %	CaO	55.71 %	
Al <sub>2</sub> O <sub>3</sub>	0.030 %	L.O.I.	43.20 %	

## PHYSICAL PROPERTIES OF THE RAW MATERIAL

DENSITY	2650 Kg/m
HARDNESS (Moh,s Scale)	3
REFRACTIVE	1.59
PARTIAL SHAPE	Crystalline "Rhomb <sup>3</sup> ohedral"

## TECHNICAL DATA OF THE PROUCED MATERIAL

MOISTURE WHEN PACKED	0.15 %	(ISO 787/2)
(PH) VALUE	8.7	(ISO 787/9)
OIL ABSORPTION	17g /100g	(ISO 787/5)
WHITENESS (Y) VALUE	95.5	(ASTM 313) ( Drick, 103C, Data color)
BRIGHTNESS	92.96	(ASTM 313) ( Drick, 103C, Data color)

## FINESS (Malvern 3000, master sizer)

RESIDUE ON 40 µm	0.01 %	(ISO 787/2)
TOP CUT (D 98)	55 µm	(ISO 787/2)
MAIN PARTICLE SIZE (D 50)	8µm	

## APPLICATIONS

Paint : Interior and exterior paints.

Rubber : automotive products, household products, tubing closures and other areas of manufacture.

Misc : used in putty, bath tub sealers, body deadeners and adhesives, plastics, polyester fiberglass premixes, Preforms and hand lay-up gel coats.

## Delivery

- Dispatches Is Made Direct From The Producing Work In Amman-jordan And Immediate Delivery Is Available To Reach Our Customers Anywhere.
- Standard Packing Is Multi -ply Non-returnable Paper Bags Of 25kg In Pallets (As Per Customers Specification).
- For Other Grades Please See Complete Set Of Datasheets For Any Additional Information Please Do Not Hesitata To Contact Us.